

AMENDMENTS TO THE CLAIMS:

Kindly cancel claims 1 and 14, amend claims 2-12, 15-22 and 24 and add new claims 26 and 27, as shown below.

This listing of claims will replace all prior versions and listings of claims in the Application:

Claim 1 (cancelled)

Claim 2 (currently amended): ~~The battery as claimed in claim 1,~~ A battery comprising :

a battery element including a non-aqueous electrolyte ;

a film case having at least a sealant polymer resin film for sealing said battery element ;

at least a lead terminal extending from said battery element and projecting from said film case, and said lead terminal with a surface having a contact area in contact directly with said sealant polymer resin film, and at least said contact area of said surface of said lead terminal is coated with an anti-corrosion coating film,

wherein said anti-corrosion coating film includes :


(A) a polymer of structural units of a phenolic compound, and at least a part of said structural units includes a substituent which comprises an amino group or a substituted amino group ;

(B) a phosphate compound ; and



(C) a titanium fluorine compound, and wherein said anti-corrosion coating film has a thickness in the range of 5 nanometers to 1000 nanometers.

Claim 3 (currently amended): The battery as claimed in claim [[1]] 2, wherein an entirety of said surface of said lead terminal is coated with an anti-corrosion coating film.

Claim 4 (currently amended): The battery as claimed in claim [[1]] 2, wherein (A) said polymer of structural units is represented by general formula (I):




where "n" is an average polymerization degree in the range of 2 to 50, "X" is a hydrogen atom, a C₁-C₅ alkyl ~~groups~~ group or a C₁-C₅ hydroxy alkyl ~~groups~~ group, "Y" is an oxygen atom or a Z-group which is represented by either one of general formulae (II) and (III) :




where each of "R₁", "R₂" and "R₃" is independently selected from a C₁-C₁₀ alkyl groups group or a C₁-C₁₀ hydroxy alkyl groups group, and an averaged number of said Z-groups bonded to each benzene ring is in the range of 0.2 to 1.0.


Claim 5 (currently amended): The battery as claimed in claim [[1]] 2, wherein (A) said polymer of structural units is represented by general formula (IV) :




where "X¹" in each structural unit is independently selected from a hydrogen atom or a Z¹-group which is represented by general formula (V) :



where each of "R¹" and "R²" is independently selected from a hydrogen atom, a C₁-C₁₀ alkyl groups group, or a C₁-C₁₀ hydroxy alkyl groups group; and "Y¹" in general formula (IV) is selected from a hydrogen atom, a hydroxyl groups group, a C₁-C₅ alkyl groups group, a C₁-C₅ hydroxy alkyl groups group, a C₆-C₁₂ aryl groups group, a benzyl groups group or a group which is represented by general formula (VI) :



where each of “R³” and “R⁴” is independently selected from a hydrogen atom, a C₁-C₁₀ alkyl groups group, or a C₁-C₁₀ hydroxy alkyl groups group; and if “Y¹” is represented by the general formula (VI), then each “X²” is in each structural unit represented by the general formula [(IV)] (VI) is independently selected from a hydrogen atom or a Z²-group which is represented by general formula (VII) :



where each of “R⁵” and “R⁶” is independently selected from a hydrogen atom, a C₁-C₁₀ alkyl groups group, or a C₁-C₁₀ hydroxy alkyl groups group; and “Y²” in the general formula (IV) represents a hydrogen atom or a part of a condensed benzene ring including “Y¹”, “Y²” and a bonding between “Y¹” and “Y²”; and where a total rate of introducing Z¹-group and Z²-group into each benzene ring is in the range of 0.2 – 1.0.

Claim 6 (currently amended): The battery as claimed in claim [[1]] 2, wherein said (B) phosphate compound is selected from the groups group consisting of phosphoric acid,

phosphate, condensed phosphoric acid, condensed phosphate, zirconium phosphate, and titanium phosphate.

Claim 7 (currently amended): The battery as claimed in claim [[1]] 2, wherein said (C) titanium fluorine compound is selected from the group consisting of titanium hydrofluoric acid,[[,]] and titanium borofluoric acid.

Claim 8 (currently amended): The battery as claimed in claim [[1]] 2, wherein said lead terminal includes aluminum.

Claim 9 (currently amended): The battery as claimed in claim [[1]] 2, wherein said non-aqueous electrolyte includes a lithium salt of an inorganic fluoride.

Claim 10 (currently amended): The battery as claimed in claim [[1]] 2, wherein said lead terminal has two generally flat surfaces opposite to each other, and an entirety of each of said two generally flat surfaces is coated with said anti-corrosion coating film.

Claim 11 (original): The battery as claimed in claim 10, wherein said lead terminal comprises a film-structure which further comprises : a metal foil ; and said anti-corrosion coating films coating said metal foil.

Claim 12 (currently amended): The battery as claimed in claim [[1]] 2, wherein a entirety of surface said lead terminal is coated with said anti-corrosion coating films.

Claim 13 (original): The battery as claimed in claim 12, wherein said lead terminal comprises: a core structure comprising a metal foil; and said anti-corrosion coating film coating said core structure.

Claim 14 (cancelled)

Claim 15 (currently amended): ~~The lead terminal as claimed in claim 14,~~ A lead terminal connected with an electric device sealed with a film case having at least a sealant polymer resin

film for sealing said electric device, and a surface of said lead terminal having a contact area in contact directly with said sealant polymer resin film, and said contact area of said surface of said lead terminal being coated with an anti-corrosion coating film,

wherein said anti-corrosion coating film includes :


(A) a polymer of structural units of a phenolic compound, and at least a part of said structural units includes a substituent which comprises an amino group or a substituted amino group;

(B) a phosphate compound; and

(C) a titanium fluorine compound, and wherein said anti-corrosion coating film has a thickness in the range of 5 nanometers to 1000 nanometers.


Claim 16 (currently amended): The lead terminal as claimed in claim ~~[[14]]~~ 15, wherein an entirety of said surface of said lead terminal is coated with an anti-corrosion coating film.

Claim 17 (currently amended): The lead terminal as claimed in claim ~~[[14]]~~ 15, wherein (A) said polymer of structural units is represented by general formula (I) :




(I)

where "n" is an average polymerization degree in the range of 2 to 50, "X" is a hydrogen atom, a C₁-C₅ alkyl groups group or a C₁-C₅ hydroxy alkyl groups group, "Y" is an oxygen atom or a Z-group which is represented by either one of general formulae (II) and (III):



(II)




(III)

where each of "R₁", "R₂" and "R₃" is independently selected from a C₁-C₁₀ alkyl groups group or a C₁-C₁₀ hydroxy alkyl groups group, and an averaged number of said Z-groups bonded to each benzene ring is in the range of 0.2 to 1.0.


Claim 18 (currently amended): The lead terminal as claimed in claim [[14]] 15, wherein (A) said polymer of structural units is represented by general formula (IV):

HAYES SOLOWAY P.C.
130 W. CUSHING STREET
TUCSON, AZ 85701
TEL. 520.882.7623
FAX. 520.882.7643


175 CANAL STREET
MANCHESTER, NH 03101
TEL. 603.668.1400
FAX. 603.668.8567



where "X¹" in each structural unit is independently selected from a hydrogen atom or a Z¹-group which is represented by general formula (V) :




where each of "R¹" and "R²" is independently selected from a hydrogen atom, a C₁-C₁₀ alkyl groups group, or a C₁-C₁₀ hydroxy alkyl groups group; and "Y¹" in general formula (IV) is selected from a hydrogen atom, a hydroxyl groups group, a C₁-C₅ alkyl groups group, a C₁-C₅ hydroxy alkyl groups group, a C₆-C₁₂ aryl groups group, a benzyl groups group or a group which is represented by general formula (VI) :



where each of "R³" and "R⁴" is independently selected from a hydrogen atom, a C₁-C₁₀ alkyl groups group, or a C₁-C₁₀ hydroxy alkyl groups group; and if "Y¹" is represented by the general formula (VI), then each "X²" is in each structural unit represented

by the general formula $[(IV)]$ (VI) is independently selected from a hydrogen atom or a Z^2 -group which is represented by general formula (VII) :



where each of “R⁵” and “R⁶” is independently selected from a hydrogen atom, a C₁-C₁₀ alkyl ~~groups~~ group, or a C₁-C₁₀ hydroxy alkyl ~~groups~~ group; and “Y²” in the general formula (IV) represents a hydrogen atom or a part of a condensed benzene ring including “Y¹”, “Y²” and a bonding between “Y¹” and “Y²”; and where a total rate of introducing Z¹-group and Z²-group into each benzene ring is in the range of 0.2 – 1.0.

Claim 19 (currently amended): The lead terminal as claimed in claim $[[14]]$ 15, wherein said (B) phosphate compound is selected from the ~~groups~~ group consisting of phosphoric acid, phosphate, condensed phosphoric acid, condensed phosphate, zirconium phosphate, and titanium phosphate.

Claim 20 (currently amended): The lead terminal as claimed in claim $[[14]]$ 15, wherein said (C) titanium fluorine compound is selected from the group consisting of titanium hydrofluoric acid, $[[,]]$ and titanium borofluoric acid.

Claim 21 (currently amended): The lead terminal as claimed in claim $[[14]]$ 15, wherein said lead terminal includes aluminum.

Claim 22 (currently amended): The lead terminal as claimed in claim [[14]] 15, wherein said lead terminal has two generally flat surfaces opposite to each other, and an entirety of each of said two generally flat surfaces is coated with said anti-corrosion coating film.

Claim 23 (original): The lead terminal as claimed in claim 22, wherein said lead terminal comprises a film-structure which further comprises : a metal foil ; and said anti-corrosion coating films coating said metal foil.

Claim 24 (currently amended): The lead terminal as claimed in claim [[14]] 15, wherein a entirety of surface said lead terminal is coated with said anti-corrosion coating films.

Claim 25 (original): The lead terminal as claimed in claim 24, wherein said lead terminal comprises : a core structure comprising a metal foil ; and said anti-corrosion coating film coating said core structure.

Claim 26 (new): The battery as claimed in claim 2, wherein said thickness of said anti-corrosion coating film is in the range of 50 nanometers to 500 nanometers.

Claim 27 (new): The battery as claimed in claim 15, wherein said thickness of said anti-corrosion coating film is in the range of 50 nanometers to 500 nanometers.

HAYES SOLOWAY P.C.
130 W. CUSHING STREET
TUCSON, AZ 85701
TEL. 520.882.7623
FAX. 520.882.7643

175 CANAL STREET
MANCHESTER, NH 03101
TEL. 603.668.1400
FAX. 603.668.8567